

IMPACT TESTING ON SAFETY GLAZING MATERIAL

Rendered to:

GLAS-WULFMEIER GMBH
Eckendorfer Strasse 45-47
D-33609 Bielefeld
Germany

Report No: 92729.07-301-37
Test Date: 06/02/09
Report Date: 07/21/09

Sample ID.: Prototype 1/4" Tempered Transparent Glass
Samples Obtained from Manufacturer: Glas-Wulfmeier GmbH - Bielefeld, Germany
Size Classification: Unlimited
Lab Temperature: 73°F
Duration of Pre-Conditioning @ 65 - 85°F: 72 Hours
Test Size: 34" wide by 76" high
All test specimens were destroyed by test or by our personnel and have been disposed of as trash.

Impact Tests: (ANSI Class A / CPSC Category II)

Spec. No.	Test Standard	Thickness, inches	Impact Drop Height, inches	Test Results, grams	Acceptance Criteria, grams	Pass / Fail Results
1	ANSI Z97.1-2004	0.234	48	13	96	Pass
2	ANSI Z97.1-2004	0.235	48	19	97	Pass
3	ANSI Z97.1-2004	0.233	48	16	96	Pass
4	ANSI Z97.1-2004	0.233	48	13	96	Pass
5	CPSC 16 CFR 1201 ⁽¹⁾	0.235	48	12	97	Pass

¹ Effective July 1977

Conclusion: Meets the requirements of the referenced standards.

For ARCHITECTURAL TESTING:

Kenny C. White
Laboratory Manager

Scott T. Swaltek, P.E.
Senior Project Engineer

KW:he/alb

Detailed drawings, data sheets, representative samples of test specimens, a copy of this test report, and all other supporting evidence will be retained by Architectural Testing, Inc. for a period of four years from the original test date. At the end of this retention period, said materials shall be discarded without notice, and the service life of this report by Architectural Testing shall expire. Results obtained are tested values and were secured using the designated test methods. This report neither constitutes certification of this product nor expresses an opinion or endorsement by this laboratory; it is the exclusive property of the client so named herein and relates only to the tested specimens. This report may not be reproduced, except in full, without the written approval of Architectural Testing, Inc.

Revision Log

<u>Rev. #</u>	<u>Date</u>	<u>Page(s)</u>	<u>Revision(s)</u>
0	07/21/09	N/A	Original report issue